

Characteristics

EPC / Grün - SK is a stoneware body suitable for dry pressing.
Available as spray dried granulate.

Firing Colour	light green		
Recommended Firing Temperature Range	1000	-	1220 °C

Technical Data

Unfired

Moisture	7,0%							
Chemical Analysis	SiO ₂	TiO ₂	Al ₂ O ₃	Fe ₂ O ₃	CaO	MgO	K ₂ O	Na ₂ O
	72,0%	0,50%	22,1%	0,60%	0,60%	0,40%	2,80%	0,85%
Loss of Ignition	5,8%							
	>500µm	>400µm	>315µm	>200µm	>100µm	<100µm		
	20,0%	28,0%	25,0%	20,0%	4,0%	0,3%		

Fired

Specimen Firing Temperature [°C]	1140
Coefficient of Thermal Expansion [x10-6/°C]	
20 - 400 °C	6,3
20 - 500 °C	6,7
20 - 600 °C	7,6
Dry to Fired Shrinkage [%]	7,2
Water Absorption [%]	2,5

The technical data quoted on this sheet is indicative only. Any sale is by sample and is governed by our general conditions of sale.



KERAMISCHE MASSEN

04.03.2016



Amtsgericht Montabaur HRB 1581, Sitz der Gesellschaft 56235 Ransbach-Baumbach

Sibelco Deutschland GmbH
Sälzerstraße 20, 56235 Ransbach-Baumbach, Germany
Tel. +49 (0) 2623 83-0, Fax +49 (0) 2623 83-1499
Geschäftsführer Michael Klaas
www.sibelco.eu